



GENERAL GUIDE FOR THE LAUNDERING OF PRINTED FLOOR RUGS

Material composition of rugs

87 % Nitrile Rubber

13 % Polyester

We recommend that a detergent between pH7.0 (Neutral) and pH9.0 (Maximum) is used.

Process	Temp	Chemical Additions
Wash (Eco)	30°C	Normal Cycle - Non-Ionic Detergent
Tumble Dry/Extract		15 mins at 60°C
Alternatively rugs may be line dried		

Important

We strongly advise that all chemicals used when washing the rugs do not contain any Optical Brightening Agents (OBA's). Optical Brightening Agents have the ability to mask the true shade of the colour and make it appear that the rug is losing dye.

Mineheart cannot be responsible for any problem associated with colour change, which is due to the use of detergents containing OBA's or Fluorescing Agents.

- Do not wash rugs alongside other rug types in order to minimise dye migration.
- Do not use Chlorine based products.

Drying Instructions

- Times may vary depending on the efficiency of the machine extraction, volume of mats, ambient temperature and steam pressure.
- Over-drying can also have an effect on the absorbency of the fibre making it less absorbent.
- It is not recommended leaving mats in a creased/warm condition in the tumbler once the process has finished, remove from the tumbler immediately and lie flat or roll.
- It is not recommended stacking face to face and always roll with the face innermost.
- It is not recommended folding mats. The resultant creases may crack and cause the rubber to perish.
- Tumble drying helps to remove any grit left in the mat after the wash process.